



### Glass Boards M-550

		Multitherm 550
Classification Temperature, °C		500
Colour		white
Density, kg/m <sup>3</sup>		130
Linear Shrinkage (after 24 hours at 450°C)		<1
Thermal Conductivity, W/m.K		
	100°C	0,029
	200°C	0,032
	300°C	0,036
	400°C	0,042
Standard Sizes, mm		1000x500, 1200x1000
Available Thicknesses, mm		3-5-10-12-15-20-25-30
Manufacturer		Techno-Physik

*Multitherm 550, made of glass fibres, is easily tooled and employed. It has high insulating power and low weight  
Classification Temperature: 500°C*